

OK TO ENTER: /J.M./

IN THE CLAIMS

1. (Previously presented) An aluminium alloy product with high strength and fracture toughness and a good corrosion resistance, said alloy consisting of, in weight %:

Zn	7.2 to 7.43
Mg	1.92 to 2.1
Cu	1.43 to 1.80
Zr	about 0.06 to 0.1
Fe	< about 0.08
Si	< about 0.07
Mn	0.05 to 0.11

and other impurities or incidental elements each < 0.05, total < 0.15, and the balance being aluminium.

2-6. (Cancelled)

7. (Previously presented) Aluminium alloy product according to claim 1, wherein
Mg 1.92 to 1.95.

8. (Currently amended) Aluminium alloy product according to claim 1, wherein
Mg 1.92 to 1.95
Cu 1.43 to 1.75.

9-27. (Cancelled)

28. (Previously presented) An aluminium alloy product according to claim 1, said alloy consisting of, in weight %:

Zn	7.2 to 7.43
Mg	1.92 to 2.1
Cu	1.43 to 1.75
Zr	about 0.06 to 0.10